

RAW MATERIAL SPECIFICATIONS						
	Stock Thickness	Temper	Coating			
	Stock	HIICKHGSS	remper	Inside	Outside	
BODY	TFS	.0091"	T3CA	PET film	PET film	
воттом	TFS	.0130"	T5CA	PET film	PET film	

PRESSURE RESISTANCE			
Buckle	Burst		
MIN	MIN		
218 psig	270 psig		
15 bar	18.6 bar		

(DOT 2Q & 15 BAR Rated)

